



**SICARO**

# Sicaro Safariwood Shadow Gap Cladding


Datasheet January 2026- Version 1



Sicaro Safariwood Shadow Gap Cladding



Product codes: S-SWGC-8891-01-AA/C  
S-SWGC-13819-01-AA/C



Product description

Sicaro products are made from sustainable FSC® certified New Zealand Radiata timber that has been fortified using proprietary water-based formulations impregnated all the way through the timber and when cured provide locked in weight, strength, hardness, color and durability without the use of any biocides.

Sicaro Safariwood is a quartersawn product and will have a straight grain appearance.

|                    |                                                                                                                                                                                                                                                                           |
|--------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Profile:           | Smooth topside, hidden fix, shadow gap profile                                                                                                                                                                                                                            |
| Dimensions:        | 3.46" × 0.75", 5.43" × 0.75"                                                                                                                                                                                                                                              |
| Standard lengths:  | 7' 10" – 15' 9" full length, defect free face                                                                                                                                                                                                                             |
| Cupping:           | Maximum 1% of width                                                                                                                                                                                                                                                       |
| Moisture content:  | 8-12% from production                                                                                                                                                                                                                                                     |
| A/B faced decking: | Both faces may occasionally have surface cracks or pitch pockets but this will not effect the performance of the product. The reverse side of the board may have a color blemish, rough finish or production marks but this will not eect the performance of the product. |

Technical data

|                   |                                                                   |
|-------------------|-------------------------------------------------------------------|
| Density:          | 43.07 lb/ft³                                                      |
| Hardness:         | ASTM D1037-12 - 1,536 lbf Janka                                   |
| Fire performance: | ASTM-E84 Class A                                                  |
| Durability:       | CEN/TS 15083-1, Class 1 outdoors above ground, Highest Durability |
| Use class:        | Class 3 outdoors above ground                                     |
| Emissions:        | EN ISO 12460-5:2015 Super E0, Ultra Low, better than CARB Phase 2 |



The mark of  
responsible forestry  
FSC® C152134



Locked in  
Performance



Recyclable



Non Toxic  
Recyclable



Durability



Fire Standard



Guarantee

## Colours

---



**Ticari**  
warm golden teak



**Livada**  
rich brown rosewood



**Azarac**  
dark strong ebony

---

## Color Maturation

---

The timber fortification process locks performance and color all the way through to the core of all Sicaro product and without a protective coating Sicaro products will mature to a gray patina over time.

These images show Sicaro Ticari once installed, the same product 2 years later and then washed 3 years after installation without any protective treatment being applied. Please note that after cleaning unprotected product color will be revealed although the tone will have changed compared to newly installed product. This color change is determined by environmental factors and will therefore differ from region to region and application to application with exposure to the elements over the product service life.



**Ticari newly  
installed**

**Ticari aged  
after 2 years  
installation**

**Ticari washed  
after 3 years  
installation**

## Caring for your Sicaro products

---

If your Sicaro products have been left to silver they can be washed or lightly sanded to reveal color that can be enhanced and protected using a good quality oil. It is recommended that only penetrating products are used especially on decking to prevent a surface film that could reduce the products grip resistance when wet.

Where an oil has been applied during installation then re-coating will be required in accordance with the coating supplier's instructions.

However it is important to remember that:

- the quality of surface preparation and the condition of the old coating will determine how good the recoating looks and how well it will last
- take time preparing the surface before re-coating
- better quality coatings will last longer and look better, so spend the money to buy the best coating product you can afford
- apply the number of coats recommended by the coating supplier.

## Disclaimer

---

Sicaro products are made from natural timber that will have variation so all technical data is an average. All products should be installed by an experienced or qualified professional and best practice always followed when installing these products.

The color of this product will change over time and the manufacturer Biotanex New Zealand Limited can not be held responsible for this however it will not effect the overall performance of the product, additional care and maintenance guides are available at [sicaro.info](http://sicaro.info)

This information relates specifically to the products listed and alterations to the specifications may effect the technical performance.

Biotanex New Zealand Limited is continuously working on technology and product development, information in this product datasheet may therefore be changed without further notice.

---

